
Cualitative Filter Papers

Grade:	HQL-06
Weight [g/m²]	85
Thickness [mm]	0,17
Filtration speed [s]	140
Surface	smooth / glatt
Ash content (%)	0,1
Average retention capacity [µm]	2- 4

Applications and properties / Slow filtration, for fine and very fine precipitates.